



## High Tenacity Polyester Filament Yarns For Your Special Technical Applications

Why settle for regular tenacity polyester for your medical devices and components when you can have high tenacity to...

- increase strength
- reduce profiles
- increase design safety margins

Item	Titer <sup>1</sup> (Denier)	Filaments	Tenacity <sup>2</sup> (g/d)	Elongation (%)	HAS @177°C (%)	Package Wt. (Kg)	Package Type
30/12-HTPET-WF	30	12	8.0	15.0	2.2	2.0	Cheese
40/18-HTPET-WF	40	18	8.0	15.0	2.2	0.5	Cone
50/24-HTPET-WF	50	24	8.0	15.0	2.2	0.5	Cone
70//30-HTPET-WF	70	30	8.0	15.0	2.2	0.5	Cone
100/36-HTPET-WF	100	36	8.0	15.0	2.2	0.5	Cone
150/48-HTPET-WF	150	48	8.0	15.0	2.2	0.5	Cone
210/72-HTPET-VT	210	72	8.0	15.0	7.0	1.0	Tube
500/96-HTPET-VT	500	96	8.5	15.0	7.0	1.0	Tube
1000/192-HTPET-VT	1000	192	9.0	15.0	7.0	1.0	Tube

1. Titer Conversion:  $Dtex = Denier \div 0.9$
2. Tenacity Conversion:  $cN/dtex = g/d \div 1.133$

**DISCLAIMER:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as TDA deems appropriate.